

Product Information Bulletin

2012 BCBC - PlastiSpan® Insulation for Interior Basement Applications

Page 1 of 4

A Canada Mortgage and Housing Corporation (CMHC)/Canadian Home Builders Association (CHBA) report concluded that use of insulation partway down the interior of a basement wall, as is typical for many residential applications, actually increases heat loss to the adjacent soil because the upper zone insulation is appreciably short-circuited by the heat loss from below.

PlastiSpan® insulation is a rigid closed cell, expanded polystyrene (EPS) insulation. It is an ideal solution to provide full-height interior basement wall insulation. Table 1 below provides material properties for PlastiSpan insulation material.

Table 1 – PlastiSpan Insulation – CAN/ULC-S701, Type 1 Material Properties

Material Property ¹	ASTM Test Method	Units	PlastiSpan Insulation
Thermal Resistance <i>Minimum per 25 mm (inch)</i>	C518	m ² ·°C/W (ft ² ·h·°F/BTU)	0.65 (3.75)
Compressive Resistance <i>Minimum @ 10% Deformation</i>	D1621	kPa (psi)	70 (10)
Flexural Strength <i>Minimum</i>	C203	kPa (psi)	170 (25)
Water Vapour Permeance² <i>Maximum</i>	E96	ng/(Pa·s·m ²) (Perms)	300 (5.0)
Water Absorption³ <i>Maximum</i>	D2842	% By volume	6.0
Dimensional Stability <i>Maximum, 7 Days @ 70 ± 2 °C (158 ± 4 °F)</i>	D2126	% Linear Change	1.5
Limiting Oxygen Index <i>Minimum</i>	D2863	%	24

This bulletin highlights some of the typical details that should be considered when using **PlastiSpan** insulation for this application.

1. **PlastiSpan** insulation properties are third party certified to CAN/ULC-S701, **Standard for Thermal Insulation, Polystyrene, Boards and Pipe Covering**, under a certification program administered by Intertek and are listed by the Canadian Construction Materials Centre (CCMC) under evaluation listing number 12424-L.
2. WVP values quoted are maximum values for 25-mm thick samples with natural skins intact. Lower values will result for thicker materials.
3. The water absorption laboratory test method involves complete submersion under a head of water for 96 hours. The water absorption values above are applicable to specific end-use design requirements only to the extent that the end-use conditions are similar to test method requirements.

As indicated in Table 1, **PlastiSpan** insulation has a maximum vapour permeance of 300 ng/Pa·s·m² for a 25 mm (1") thickness. Therefore, a separate vapour barrier on the warm side of the insulation would be required in wall assemblies using **PlastiSpan** insulation at a thickness less than 125 mm (5").

2012 BCBC – Energy Efficiency Requirements

2012 BCBC, Section 9.36 provides energy efficiency requirements for buildings 3 storeys or less in building height, having a building area not exceeding 600 m² and used for major occupancies classified as residential occupancies.

Energy efficiency requirements in 2012 BCBC, Subsection 9.36.2. are based upon minimum **effective thermal resistance (RSI_{eff}/R_{eff})** of building assemblies which includes the effect of thermal bridging due to repetitive structural members such as wood framing members in wall or roof assemblies calculated using the following formula.

$$RSI_{eff} (R_{eff}) = \frac{100\%}{\frac{\% \text{ with Framing}}{RSI_F (R_F)} + \frac{\% \text{ Area Cavity}}{RSI_C (R_C)} + RSI(R) \text{ Continuous Material Layers}}$$

Table 2 provides **RSI_{eff} (R_{eff})** for basement walls per 2012 BCBC, Tables 9.36.2.8.A. (for buildings without a heat-recovery ventilator) and 9.36.2.8.B. (for buildings with a heat-recovery ventilator).

Table 2 - Minimum RSI_{eff} (R_{eff}) – Basement Walls Below or In Contact with Ground

2012 BCBC Climate Zones	Zone 4	Zone 5	Zone 6	Zone 7a	Zone 7b	Zone 8
Heating Degree-Days (HDD) Celsius Degree-Days	< 3,000	3,000 to 3,999	4,000 to 4,999	5,000 to 5,999	6,000 to 6,999	≥ 7,000
Table 9.36.2.8.A. Effective Thermal Resistance						
RSI _{eff} - m ² ·°C/W	1.99	2.98	2.98	3.46	3.46	3.97
R _{eff} - ft ² ·hr·°F/BTU	11.3	16.9	16.9	19.6	19.6	22.5
Table 9.36.2.8.B. Effective Thermal Resistance						
RSI _{eff} - m ² ·°C/W	1.99	2.98	2.98	2.98	2.98	2.98
R _{eff} - ft ² ·hr·°F/BTU	11.3	16.9	16.9	16.9	16.9	16.9

Table 3 provides annual heating degree days for some building locations in Climate Zones 4 to 7a as per 2012 BCBC, Division B, Appendix C.

Table 3 - Annual HDD (Celsius Degree Days) for Building Locations

Climate Zone 4		Climate Zone 5		Climate Zone 6		Climate Zone 7a	
Locations	HDD	Locations	HDD	Location	HDD	Locations	HDD
Duncan	2980	Hope	3000	Cranbrook	4400	100 Mile House	5030
Victoria	2650	Nanaimo	3000	Golden	4750	Smithers	5040
West Vancouver	2950	Burnaby	3100	Terrace	4150	Dawson Creek	5900
Abbotsford	2860	Kamloops	3450	Whistler	4180	Mackenzie	5550
Chilliwack	2780	Kelowna	3400	Prince George	4720	Glacier	5800

Table 4 provides the **RSI_{eff} (R_{eff})** for a basement wall assembly using **PlastiSpan** insulation to provide a continuous insulation layer over the interior of the basement wall to meet minimum requirements for 2012 BCBC Climate Zone 4.

Table 4 – PlastiSpan Insulation Interior Basement Example – 2012 BCBC Climate Zone 4

System Description	RSI _F	RSI _C	Continuous Materials
203 mm (8") Basement wall	----	----	0.08
102 mm (2.5") PlastiSpan Insulation	----	----	1.65
Wood Strapping @ 600 mm (24")	0.54	----	----
13 mm (1/2") Gypsum wall board	----	----	0.08
Inside Air Film	----	----	0.12
Total	0.54	NA	1.93
% Area of Each Component	13%	NA	100%
RSI_{eff} (R_{eff})		RSI-2.00 (R11.4)	

Table 5 provides the **RSI_{eff} (R_{eff})** for a basement wall assembly using **PlastiSpan** insulation board to provide a continuous insulation layer over the interior of the basement wall to meet minimum requirements for 2012 BCBC, Table 9.36.2.8.A. for Climate Zones 5 to 6 & Table 9.36.2.8.B. for Climate Zones 5 to 8.

Table 5 – PlastiSpan Insulation Interior Basement Example – 2012 BCBC Climate Zones 5 to 8

System Description	RSI _F	RSI _C	Continuous Materials
203 mm (8") Basement wall	----	----	0.08
102 mm (4") PlastiSpan Insulation	----	----	2.64
Wood Stud @ 600 mm (24")	0.54	----	----
13 mm (1/2") Gypsum wall board	----	----	0.08
Inside Air Film	----	----	0.12
Total	0.54	NA	2.92
% Area of Each Component	13%	NA	100%
RSI_{eff} (R_{eff})		RSI-2.99 (R17.0)	