

# Product Information Bulletin

BULLETIN NO.	213
ISSUED:	September 12, 2017
REPLACES:	January 5, 2016

## PlastiSpan® 25 Insulation - CAN/ULC-S701, Type 3 Material Properties

**PlastiSpan® 25** insulation is a rigid, closed-cell insulation that meets or exceeds requirements for expanded polystyrene (EPS) insulation manufactured to CAN/ULC-S701, Type 3. The table below provides material properties for **PlastiSpan 25** insulation.

Material Properties <sup>1</sup>	Units	Values
<b>Thermal Resistance</b> <i>Minimum per 25 mm (1 inch)</i> ASTM C518	m <sup>2</sup> ·°C/W (ft <sup>2</sup> ·h·°F/BTU)	0.74 (4.27)
<b>Compressive Resistance</b> <i>Minimum @ 10% Strain</i> ASTM D1621	kPa (psi)	170 (25)
<b>Flexural Strength</b> <i>Minimum</i> ASTM C203	kPa (psi)	300 (44)
<b>Water Vapour Permeance<sup>2</sup></b> <i>Maximum</i> ASTM E96	ng/(Pa·s·m <sup>2</sup> ) (Perms)	130 (2.25)
<b>Water Absorption<sup>3</sup></b> <i>Maximum</i> ASTM D2842	% By volume	2.0
<b>Dimensional Stability</b> <i>Maximum</i> ASTM D2126	% Linear Change	1.5
<b>Limiting Oxygen Index</b> <i>Minimum</i> ASTM D2863	%	24
<b>Surface Burning Characteristics</b> <i>Rating or Classification</i> CAN/ULC S102.2	Flame Spread	290
	Smoke Developed	Over 500

### Sustainability

As part of its commitment to ongoing sustainability initiatives, Plasti-Fab maintains **GREENGUARD Gold Certification** for **PlastiSpan 25** insulation with UL Environment, an independent global safety science organization. The **GREENGUARD Gold Certification** mark on **PlastiSpan 25** insulation gives assurance that insulation designed for use in indoor spaces meets strict chemical emissions limits, which contribute to the creation of healthier interiors.

<sup>1</sup> **PlastiSpan 25** insulation properties are third party certified to CAN/ULC-S701, **Standard for Thermal Insulation, Polystyrene, Boards, and Pipe Covering**, under a third party certification program (see Intertek Code Compliance Research Report CCRR-1072 for additional information) and is listed by the Canadian Construction Materials Centre (CCMC) under evaluation listing number 12426-L (Type 3).

<sup>2</sup> WVP values quoted are maximum values for 25-mm (1-inch) thick samples with natural skins intact. Lower values will result for thicker materials.

<sup>3</sup> The water absorption laboratory test method involves complete submersion under a head of water for 96 hours. The water absorption values above are applicable to specific end-use design requirements only to the extent that the end-use conditions are similar to test method requirements.